

QFS Pressed bends

QFS pressed bends with radius $1,5 \times$ diameter to the centerline



QFS Pressed bends

QFS Pressed bends

[ItemMaterialThickness]	0,9mm
Sluttyp A	QF
Center Line Radius (CLR)	1,5

Modeller

	Art.nr	Diameter A	Vinkel grad	Vikt
	8210000238	80	90	0,5
	8210000243	100	90	0,8
	8210000248	125	90	1,1
	8210000253	140	90	1,1
	8210000258	150	90	1,1
	8210000263	160	90	1,2
	8210000268	180	90	1,6
	8210000273	200	90	2,65
	8210000278	224	90	2,4
	8210000283	250	90	3
	8210000288	300	90	3,2
	8210000293	315	90	5
	8210000237	80	60	0,3

Modeller

	Art.nr	Diameter A	Vinkel grad	Vikt
	8210000242	100	60	0,4
	8210000247	125	60	0,8
	8210000252	140	60	0,7
	8210000257	150	60	0,7
	8210000262	160	60	0,8
	8210000267	180	60	1,2
	8210000272	200	60	1,9
	8210000277	224	60	1,7
	8210000282	250	60	1,9
	8210000287	300	60	4
	8210000292	315	60	2,5
	8210000236	80	45	0,2
	8210000241	100	45	0,3

Modeller

	Art.nr	Diameter A	Vinkel grad	Vikt
	8210000246	125	45	0,4
	8210000251	140	45	0,5
	8210000256	150	45	0,5
	8210000261	160	45	0,6
	8210000266	180	45	0,9
	8210000271	200	45	1
	8210000276	224	45	1,6
	8210000281	250	45	1,6
	8210000286	300	45	2,3
	8210000291	315	45	2,4
	8210000235	80	30	0,2
	8210000240	100	30	0,3
	8210000245	125	30	0,3

Modeller

	Art.nr	Diameter A	Vinkel grad	Vikt
	8210000250	140	30	0,5
	8210000255	150	30	0,5
	8210000260	160	30	0,5
	8210000265	180	30	0,7
	8210000270	200	30	0,9
	8210000275	224	30	1,3
	8210000280	250	30	1,5
	8210000285	300	30	2,2
	8210000290	315	30	2,2
	8210000234	80	15	0,1
	8210000239	100	15	0,2
	8210000244	125	15	0,4
	8210000249	140	15	0,4

Modeller

	Art.nr	Diameter A	Vinkel grad	Vikt
	8210000254	150	15	0,4
	8210000259	160	15	0,4
	8210000264	180	15	0,5
	8210000269	200	15	0,7
	8210000274	224	15	0,9
	8210000279	250	15	0,9
	8210000284	300	15	1,3
	8210000289	315	15	1,3